

Colori Sottocristallina

Underglaze Colours

CSC



CSC 1060
White



CSC 1078
Lemon Yellow



CSC 1030
Yellow




CSC 1009
Sun Yellow




CSC 1008
Castelli Orange



CSC 1109
Orange



CSC 1266
Coral Red



CSC 1024
Red



CSC 1049
Dark Red



CSC 1081
Flesh



CSC 1064
Pink



CSC 1101
Intensive Pink



CSC 1264
Lilac



CSC 1077
Light Violet



CSC 1265
Violet



CSC 1056
Sky Blue



CSC 1020
Turquoise



CSC 1017
Blue



CSC 1128
Dark Blue




CSC 1006
Royal Blue



CSC 1067
Petrol Blue



CSC 1004
Copper Green



CSC 1261
Grass Green



CSC 1043
Dark Green



CSC 1003
Indigo



CSC 1074
Apple Green



CSC 1085
Pea Green



CSC 1002
Green



CSC 1068
Light Brown



CSC 1015
Red Brown



CSC 1013
Brown



CSC 1114
Dark Brown



CSC 1014
Manganese



CSC 1051
Black



CSC 1082
Light Grey



CSC 1059
Grey

Formato - Size	100 g. (0,22 lbs.)	500 g. (1,10 lbs.)
Confezioni - Packaging	1	1

La serie **CSC** rappresenta la linea tradizionale di colori sottocristallina per decorare direttamente sul biscotto.

PREPARAZIONE-APPLICAZIONE-COTTURA

Miscelare con acqua, setacciare ed applicare a pennello, spugna o tampone. Applicare una cristallina trasparente.

Applicazione ad aerografo solo per uso professionale.

Temperatura di cottura: 960°-980°C (cono Orton 08-07).

*The **CSC** series represents the traditional underglaze colours to decorate directly on the bisque.*

PREPARATION-APPLICATION-FIRING

Mix with water and apply by brush, sponge, or stamping. Sifting always recommended.

Finish with transparent glaze.

Airbrush application for professional use only.

Firing temperature: 960°-980°C (Orton cone 08-07).